

## PET FG

Physical Properties	Value	Unit	Standard
Density	1.39	g/cm <sup>3</sup>	ISO 1183
Moisture pick-up till saturation (in normal climate 23 °C / 50% r.h.)	0.30	%	ISO 62
Water absorption till saturation (in water at 23 °C)	0.50	%	ISO 62

Mechanical Properties	Value	Unit	Standard
Tensile stress at yield [ $v = 50$ mm/min]	90	MPa	ISO 527-2
Tensile stress at break [ $v = 5$ mm/min]	-	MPa	ISO 527-2
Nominal percentage elongation at break	14	%	ISO 527-2
Tensile modulus of elasticity	3600	MPa	ISO 527-2
Flexural modulus of elasticity	-	MPa	ISO 178
Ball indentation hardness (value at 30 sec.)	170	MPa	ISO 2039-1
Rockwell hardness (measured with test pieces 10 mm thick)	M 95		ISO 2039-2
Charpy impact strength (+23 °C)	> 50	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength - notched (+23 °C)	3	kJ/m <sup>2</sup>	ISO 179/1eA

Electric Properties	Value	Unit	Standard
Specific insulation resistance [ $\geq$ ]	10 <sup>13</sup>	Ohm · m	IEC 60093
Specific surface resistance [ $\geq$ ]	10 <sup>14</sup>	Ohm	IEC 60093
Dielectric constant (at 1 MHz)	3.2	10 <sup>6</sup> Hz	IEC 60250
Dielectric constant (at 100 Hz)	3.4	10 <sup>2</sup> Hz	IEC 60250
Dissipation factor (at 1 MHz)	0.014	10 <sup>6</sup> Hz	IEC 60250
Dissipation factor (at 100 Hz)	0.001	10 <sup>2</sup> Hz	IEC 60250
Dielectric strength K20/K20 (in transformer oil)	22	kV/mm	IEC 60243-1
Comparative tracking index (CTI)	600		IEC 60112

Thermal Properties	Value	Unit	Standard
Temperature for usage in air (max. short term)	160	°C	
Temperature for usage in air (max. lasting)	115	°C	
Minimum service temperature in air	-20	°C	
Heat distortion temperature (HDT A process)	75	°C	ISO 75-2
Coefficient of linear expansion (at length, 23 – 60 °C)	0.6	10 <sup>-4</sup> /K	ISO 11359
Thermal conductivity (+23 °C)	0.27	W/(K · m)	DIN 52612
Flammability according UL Standard (thickness 3 and 6 mm)	HB	Class	UL 94
Vicat softening temperature (VST/B/50)	-	°C	ISO 306
Melting point (DSC, 10 K/min)	255	°C	ISO 3146

n.br. = no break

Data stated above are average values gathered by statistical tests on a regular basis. Data above are provided for information and shall not be regarded as binding unless expressly agreed in a contact of sale.